
FOREIGN TECHNOLOGY DIVISION



METHOD OF DETERMINING THE SEDIMENTATION TENDENCY OF LUBRICATING OILS


by

K. K. Papok and V. P. Danilin



The property of the second control of the se

The state of the s



This translation was made to provide the users with the basic essentials of the original document in the shortest possible time. It has not been edited to refine or improve the grammatical accuracy, syntax or technical terminology.

. ma

UNEDITED ROUGH DRAFT TRANSLATION

METHOD OF DETERMINING THE SEDIMENTATION TENDENCY OF LUBRICATING OILS

By: K. K. Papok and V. P. Danilin

English pages: 2

SOURCE: Patent No. 154439 (Appl. No. 748482/23-5,

October 19, 1961), 1 page.

Translated by: E. Harter/TDBXT

THIS TRANSLATION IS A REMDITION OF THE ORIGINAL POREIGN TEXT VITHOUT ANY ANALYTICAL OR EDITORIAL COMMENT. STATEMENTS OR THEORIES ADVOCATED OR IMPLIED ARE THOSE OF THE SOURCE AND BO NOT NECESSARILY REFLECT THE POSITION OR OPIMON OF THE POREIGN TECHNOLOGY DIVISION.

PREPARED BY

TRANSLATION DIVISION
FOREIGN TECHNOLOGY DIVISION
WP-AFB, ONIO.

TA7 5 3

ITIS INDEX CONTROL FORM

01 Acc Nr 68 Translation Nr TA7000476 FTD-UT-23-681-6			76 Reel/Frame Nr 0897 0885	
97 Header Clas 63 Clas 64 Control M	arkings		94 Expansion	40 Ctry Info
UNCL O O				U R
02 Ctry 03 Ref 04 Yr 05 Vol	06 Iss	07 B. Pģ	. 45 E. Pg.	10 Date
TF 0000 00 000	600	0001	0051	190СТ61
Transliterated Title				
TPOSEB OPREDELENIYA NAGARNOSTI SM.	AZOCHNYKH MASE	L		
09 English Title METROL OF DETERMINING THE SEDIMENTATION TENDENCY OF LUBRICATING OILS				
43 Source				
FATERY 154439 (748482/23-5) CLASS G Oln; 421, 704; C 10m; 23c, 101 (Russian)				
42 Author	98 Document Location			
PAPOK, K. K.				
16 Co-Author	47 Subject Codes			
FAMILIA, V. P.	07, 11			
16 Co-Author	39 Topic Tags: lubricating oil,			
HONE	sedimentation separation, test method			
16 Co-Author				
HORE				
16 Co-Author NONE				

ABSTRACT: A method of determining the tendency of lubricating oils to leave a deposit which has the distinguishing feature that a batch of the tested oil is put into a crucible which is then put into a lacquer maker heated up to from Fig. to 500°C and kept at this temperature until the giving off of the valuable components of the oil has stopped, after which the crucible is cooled and the amount of sooty residue is weighed. () English Translation: 2 pages.

FTD FEE 67 0-90

METHOD OF DETERMINING THE SEDIMENTATION TENDENCY OF LUBRICATING OILS

K. K. Papok and V. P. Danilin

At the present time the tendency of lubricating oils to form soot or sediment is judged by their coking qualities. The direct determination of this tendency of oils is proposed for the first time.

A crucible with a weighed portion of 0.2 g of oil to be tested is placed in a lacquer maker at the temperature of 350 to 500°C. After the stopping of the evaporating of the oil the crucible is kept at the given temperature until the complete discontinuance of the separation of the volatile components of the oil. Then the crucible is covered with a lid, taken from the disk, and cooled to room temperature, and then weighed. The amount of sediment is expressed in percent of the batch of tested oil.

Object of the Invention

A method of determining the tendency of lubricating oils to leave a deposit which has the distinguishing feature that a batch of the tested oil is put into a crucible which is then put into a lacquer maker heated up to from 350 to 500°C and kept at this temperature until the giving off of the volatile components of the oil has

The second second

stopped, after which the crucible is cooled and the amount of sooty residue is weighed.